

Aspirating Pipe and Fittings

VESDA PIPE

General Information

- Always use tools specifically designed for plastic pipe.
- Protective gloves are recommended for use when solvent cementing. If hands come into contact with cement, use a waterless abrasive soap.
- Avoid sources of heat or open flames when solvent cementing. Do not smoke.
- Always chamfer and deburr pipe ends.
- Use the proper solvent cement (note; air shipments of solvent cement are forbidden by law).
- Always replace lids on cans when not in use.
- Never dilute solvent cement.
- Keep jointing surfaces dry in wet weather.
- Avoid direct inhalation of fumes. Use in a well-ventilated area.
- Wipe up spills or leaks immediately with clean lint free cloth or paper towels.
- Follow recommended cure times prior to testing the system.
- Prevent excessive solvent cement from running into the pipe or fitting socket.



The Integrity of air sampling systems may be affected if proper CPVC solvent cement is not used. Xtralis disclaims responsibility for any air sampling pipe system constructed with cements other than those recommended.

Installation Instructions

Main sampling pipes (3/4") diameter shall be installed as follows:

- Air sampling pipe network calculations shall be provided by Xtralis or a Certified VESDA distributor.
- All solvent cemented connections shall be assembled in accordance with Xtralis recommendations.
- Maximum support spacing for main sampling pipes shall not exceed 5 ft. Hangers and supports used shall be free of rough or sharp edges and shall not bind the pipe from movement.
- End caps shall be solvent cemented to each main sampling pipe, and drilled with a hole as specified by the ASPIRE2 Modelling Program.
- Sampling holes shall be 5/64" diameter, or otherwise appropriately sized to achieve the specified system performance as specified and calculated by the system design.
- Sampling points shall not be spaced at more than 30 ft intervals.
- Each Sampling Point shall be identified with a label.
- Minimum OD of all Capillary tube shall be 3/8".
- Maximum length of any Capillary tube shall not exceed 20 ft.
- The Capillary tube shall terminate at an approved ceiling sampling point.

Quality

Air Sampling Pipe and Fittings

- Manufactured in Strict accordance with ASTM F442 to SDR 13.5 dimensions.
- Fittings per ASTM F438; solvent cement per D2564.
- Pipe and fitting materials per ASTM D1784; NSF Listed Materials.

Design

- Per VESDA System Design Manual, and ;
- Local codes and standards may apply

Handling and Storage

Care should be taken at all stages of handling, transportation and storage.

- Brief exposure to direct sunlight may cause discoloration but will not affect physical properties. Piping must be covered with a non-transparent material when stored outside. This covering must provide adequate air circulation above and around the pipe as required to prevent excessive heat absorption that can result in discoloration and deformation of the product during long term storage.
- Pipe should be properly supported in storage to prevent sagging or bending. Pipe should be stored at the job site on level ground in the packages provided. Caution must be exercised to avoid compression, damage or deformation.
- Thermoplastic pipe must not be stored close to heat producing sources such as heaters, boilers, steam lines, engine exhaust etc.
- Although VESDA piping products are tough and corrosion resistant, they should not be dropped, have objects dropped on them, nor subjected to external loads. Pipe must not be dragged across the ground or over obstacles. Impacts such as dropping from sizable heights and/or rough handling should be avoided, particularly in cold weather. The product shall be inspected for any scratches, splits or gouges that may have occurred from improper handling or storage. These sections must be cut out and discarded.

VESDA[®]
by **xtralis**[™]

Aspirating Pipe and Fittings

VESDA PIPE

Solvent Cementing

Solvent cement welding is a simple and quick means of constructing high integrity leakfree joints. Care must be used to ensure that the correct solvent cement is used and that joining instructions are followed properly.

BEFORE APPLYING SOLVENT CEMENT appropriate safety precautions must be taken. Be aware at all times of good safety practices. Solvent cements are flammable. Eliminate all ignition sources. Do not smoke during use and do not expose to other sources of heat or flame in working or storage areas. Avoid breathing vapors. Use only with adequate ventilation. Explosion proof mechanical ventilation or local exhaust is recommended to maintain vapor concentrations below recommended exposure limits. In confined areas, a NIOSH approved organic vapor cartridge respirator with full-face piece is recommended. Cement should be stored in the shade at temperatures between 40°F and 110°F Containers should be kept tightly closed when not in use, and covered as much as possible during use. Avoid contact with eyes. Splash proof chemical goggles are recommended. Avoid frequent contact with skin. Wearing PVA coated gloves and an impervious apron are recommended. Solvent cements have a limited shelf life and must be used prior to the expiration date. Refer to printed warnings on cement can and Material Safety Data Sheets for additional information.

Joining Procedures

The following procedure MUST be followed:

1. The pipe must be cut square. Cutting the pipe as squarely as possible provides a maximum bonding area. VESDA pipe can be cut easily with a wheel-type plastic tubing cutter ratchet style cutter or fine toothed saw. Care must be taken not to split the pipe if a ratchet type cutter is used, particularly at colder temperatures.
2. Remove all burrs and filings, and place a slight bevel on the pipe end. A file or chamfering tool is suitable for this purpose. A proper bevel will ease entry of the pipe into the fitting socket and prevent solvent cement from being wiped from the joining surfaces during assembly.
3. Wipe loose dirt and moisture from the fitting socket and pipe end by using clean dry rag. Check the "dry fit" of the components being joined to ensure compatibility. The pipe should enter the fitting socket 1/4 to 3/4 of the way. If the pipe bottoms with little interference fit use extra solvent cement when making the joint.
4. Using the appropriate size applicator (a dauber or natural bristle brush 1/2 the size of the pipe diameter being joined) apply a heavy even coat of one-step cement to the outside pipe end while working into the surface. Apply a medium coat of cement to the fitting socket. If there was little interference during the dry fit apply a second coat of cement to the pipe end at this time. It is important to work quickly so that the cement is still liquid (to allow surfaces to slide) when pipe and fitting are assembled.
5. Immediately insert the pipe completely into the fitting socket while rotating the pipe 1/4 turn. Properly align the fitting for installation at this time. The pipe must bottom to the fitting stop. Hold the assembly for 10 to 15 seconds to ensure initial bonding. A continuous bead of cement should be evident around the joint.
6. Wipe off excessive cement with a rag (excessive cement can cause over-softening resulting in damage). The assembly must be allowed to set without any stress on the joint for 1 to 5 minutes.
7. The assemblies must be allowed to cure properly prior to use. Cure times are a function of pipe size, temperature, humidity and tightness of fit. Refer to following cure times:

Pipe Size	Temp 60°F to 120°F	Temp 40°F to 59°F	Temp 0°F to 30°F
3/4" & 1"	1 1/2 hour	4 hour	48 hour

* For estimation purposes, approximately 270 joints can be made per quart of VESDA CPVC one-step cement.

Fire Resistance

Flammability Rating	V-O UL 94 Flame Retardant
Limiting Oxygen Index	60 ASTM D2863
Flame Speed	0 ULC
Smoke Generation	0-25 ULC
Flame Travel	4 UL 1887
Optical Density	0.19 Peak 0.03 Avg. UL 1987
Heat of Combustion	7,700 BTU's/lb.

Physical

	ASTM	
Cell Classification	23447	D1784
Specific Gravity	1.55	D792
Tensile Strength	8400 psi	D638
Modulus of Elasticity	4.23 x 10 ⁵	D638
Compressive Strength	9600 psi	D695
Izod Impact	3.0	D256A
Coefficient of Linear Expansion	3.4 x 10 ⁻⁵	
Upper Temperature Limit	200°F	
Electrical Conductivity	Non-conductor	

www.xtralis.com

The Americas +1 781 740 2223 Asia +86 21 5240 0077 Australia and New Zealand +61 3 9936 7000
UK and Europe +44 1442 242 330 Middle East +962 6 588 5622

The contents of this document are provided on an "as is" basis. No representation or warranty (either express or implied) is made as to the completeness, accuracy or reliability of the contents of this document. The manufacturer reserves the right to change designs or specifications without obligation and without further notice. Except as otherwise provided, all warranties, express or implied, including without limitation any implied warranties of merchantability and fitness for a particular purpose are expressly excluded.

This document includes registered and unregistered trademarks. All trademarks displayed are the trademarks of their respective owners. Your use of this document does not constitute or create a licence or any other right to use the name and/or trademark and/or label.

This document is subject to copyright owned by Xtralis AG ("Xtralis"). You agree not to copy, communicate to the public, adapt, distribute, transfer, sell, modify or publish any contents of this document without the express prior written consent of Xtralis.

Doc. no. 14932_02

Part: 18882

VESDA[®]
by  **xtralis**[™]